

## Sika® Antisol®-E(WP)

Water based paraffin wax emulsion white pigmented curing compound

---

<b>Product Description</b>	A ready to use, liquid curing compound based on paraffin and also White Pigmented to substantially increase light reflectance to effectively prevent premature water loss from the concrete both due to heat of hydration and sunlight.
----------------------------	---

---

<b>Uses</b>	Sika® Antisol®-E(WP) is sprayed on to newly laid concrete surfaces to form a thin film barrier against premature water loss and thereby promote total cement hydration. It is particularly recommended for large areas of exposed concrete such as : <ul style="list-style-type: none"><li>■ Highways</li><li>■ Runways and taxiways</li><li>■ Aprons and hard standings</li><li>■ Roof decks</li><li>■ Canals linings.</li></ul>
-------------	---

---

<b>Characteristics / Advantages</b>	Sika® Antisol®-E(WP) provides the following benefits : <ul style="list-style-type: none"><li>■ Reduces incidence plastic cracking</li><li>■ Ensures achievement of designed strengths</li><li>■ Minimises shrinkage</li><li>■ Reduces surface dusting</li><li>■ Eliminates expensive methods of curing such as hessian-watering, etc</li></ul>
-------------------------------------	--

---

### Test

<b>Approval Standard</b>	ASTM C 309-89 Type 2 Class A
--------------------------	------------------------------

---

### Product Data

#### Form

<b>Appearance / Colours</b>	White lump free liquid
-----------------------------	------------------------

---

<b>Packaging</b>	20 kg, 100kg, 200kg
------------------	---------------------

---

#### Storage

<b>Storage Conditions / Shelf-Life</b>	6 months from date of production if stored properly in unopened original packaging at +40 to +10°C. Protect from frost and direct sun light.
--	--

---

#### Technical Data

<b>Chemical Base</b>	Aqueous Wax Emulsion and Inorganic Pigment
----------------------	--

---

<b>Relative Density</b>	0.99 - 1.02 kg/l at 25°C
-------------------------	--------------------------

---

## System Information

### Application Details

**Consumption / Dosage** 0.10 to 0.20 kg/m<sup>2</sup> depending on wind, humidity and temperature. Actual dosage to be finalised on the basis of site trials.

**Application Method/ Tools** Stir Sika<sup>®</sup> Antisol<sup>®</sup>-E(WP) well before application. Apply uniformly on to the newly laid concrete as soon as the surface water evaporates. Apply preferably using low pressure sprayer uniformly on concrete surface. Brush/Roller application could consume more Sika<sup>®</sup> Antisol<sup>®</sup>-E(WP) due to the very nature of the application.

**Notes on Application/Limitations** Remaining Sika<sup>®</sup> Antisol<sup>®</sup>-E(WP) films must be removed prior to application of any screed, plaster or coatings on the concrete surface.

**Cleaning of Tools** Clean all tools and application equipment with petrol immediately after use.

### Value Base

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

### Health and Safety Information

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Material Safety Data Sheet containing physical, ecological, toxicological and other safety-related data.

### Legal Notes

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.



Registered office:

Sika India Pvt. Ltd.  
Commercial Complex II  
620, Diamond Harbour Road  
Kolkata, 700 034, India

Phone +91 33 2447 2448/2449  
Telefax +91 33 2397 8688  
ind.sika.com  
info.india@in.sika.com